

30 SEP 2004

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
16 October 2003 (16.10.2003)

PCT

(10) International Publication Number
WO 03/085003 A1

(51) International Patent Classification⁷: C08F 2/00,
14/06, 18/08

LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,
MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG,
SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ,
VN, YU, ZA, ZM, ZW.

(21) International Application Number: PCT/IT02/00230

(22) International Filing Date: 11 April 2002 (11.04.2002)

(84) Designated States (regional): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR,
GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent
(BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR,
NE, SN, TD, TG).

(25) Filing Language: English

(26) Publication Language: English

(71) Applicant and

(72) Inventor: CARLIN, Francesco [IT/IT]; Corte Arco Vala-
resso 3, I-35100 Padova (IT).

Declaration under Rule 4.17:

— of inventorship (Rule 4.17(iv)) for US only

(74) Agents: PISTOLESI, Roberto et al.; Dragotti & Asso-
ciati SRL, Galleria San Babila, 4/C, I-20122 Milano (IT).

Published:

— with international search report

(81) Designated States (national): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.



WO 03/085003 A1

(54) Title: METHOD FOR THE APPLICATION OF ANTI-FOULING AGENTS

(57) Abstract: There is described a method for applying an aqueous solution to the internal walls of a reactor, before the start of the polymerization reaction of vinyl chloride and/or vinyl acetate, which aqueous solution contains a salt of an anti-scaling agent which comprises a product of condensation of an aldehyde, a phenolic compound and an aromatic carboxylic acid hydroxylated at the aromatic nucleus, wherein the pH-value of this aqueous solution is changed, during the application, to a pH-value of less than 5 and, preferably, in the range between 2.5 and 4.5.